

[Magnet_Property.Pdf](#) From Ningbo Vastsky Magnet Co.,Ltd. (sales@nbvsmagnetic.com, http://www.nbvsmagnetic.com)

Grade	Remanence Br				Coercivity Hcb				Intrinsic Coercivity Hcj		Max. Energy Product BH				Max. Working Temp•
	kGs		T		kOe		kA/m		kOe	kA/m	MGOe		kJ/M3		
	Min	Type	Min	Type	Min	Type	Min	Type	Min	Min	Min	Type	Min	Type	
N35	11.7	12.1	1.17	1.21	10.8	11.5	860	915	≥12	≥955	33	35	263	279	≤80
N38	12.2	12.6	1.22	1.26	10.8	11.5	860	915	≥12	≥955	36	38	287	303	≤80
N40	12.6	12.9	1.26	1.29	10.5	11	836	876	≥12	≥955	38	40	303	318	≤80
N42	12.6	13.2	1.26	1.32	10.5	11	836	876	≥12	≥955	40	42	326	342	≤80
N45	13.3	13.7	1.33	1.37	10.5	11	836	876	≥12	≥955	43	45	342	358	≤80
N48	13.7	14.1	1.37	1.41	10.5	11	836	876	≥12	≥955	46	48	367	383	≤80
N50	14.1	14.5	1.41	1.47	10.5	11	836	876	≥12	≥955	48	50	383	399	≤80
N52	14.2	15.00	1.47	1.53	10.5	11	836	876	≥12	≥955	50	52	399	415	≤80
N35M	11.7	12.1	1.17	1.21	10.8	11.5	860	915	≥14	≥1114	33	35	263	279	≤100
N38M	12.2	12.6	1.22	1.26	10.8	11.5	860	915	≥14	≥1114	36	38	257	303	≤100
N40M	12.6	12.9	1.26	1.29	10.8	11.5	860	915	≥14	≥1114	38	40	303	318	≤100
N42M	12.9	13.2	1.29	1.32	10.5	11	836	876	≥14	≥1114	40	42	326	342	≤100
N45M	13.3	13.7	1.33	1.37	10.5	11	836	976	≥14	≥1114	43	45	342	358	≤100
N48M	13.7	14.1	1.37	1.41	10.5	11	836	876	≥14	≥1114	46	48	367	383	≤100
N33H	11.4	11.7	1.14	1.17	10.3	11	820	876	≥17	≥1353	31	33	247	263	≤120
N35H	11.7	12.1	1.17	1.21	10.8	11.5	860	915	≥17	≥1353	33	35	263	279	≤120
N40H	12.6	12.9	1.26	1.29	11.5	12	915	955	≥17	≥1353	38	40	303	318	≤120
N42H	12.9	13.2	1.29	1.32	10.5	11	836	876	≥17	≥1353	40	42	326	342	≤120
N45H	13.3	13.7	1.33	1.37	10.5	11	836	876	≥17	≥1353	43	45	342	358	≤120
N30SH	10.8	11.2	1.08	1.12	9.8	10.5	780	836	≥20	≥1595	28	30	223	239	≤150
N33SH	11.4	11.7	1.14	1.17	10.3	11	820	876	≥20	≥1595	31	33	247	263	≤150
N35SH	11.7	12.1	1.17	1.21	10.8	11.5	860	915	≥20	≥1595	33	35	263	279	≤150
N38SH	12.2	12.6	1.22	1.26	11.8	12.3	939	979	≥20	≥1595	36	38	287	303	≤150
N40SH	12.6	12.9	1.26	1.29	12	12.6	955	1003	≥20	≥1595	38	40	303	318	≤150
N42SH	12.9	13.2	1.29	1.32	10.5	11	836	876	≥20	≥1595	40	42	326	342	≤150
N28UH	10.4	10.8	1.04	1.08	9.8	10.2	780	812	≥25	≥1990	26	28	207	223	≤180
N30UH	10.8	11.2	1.08	1.12	10.1	10.6	804	844	≥25	≥1990	28	30	223	239	≤180
N33UH	11.4	11.7	1.14	1.17	10.3	11	820	875	≥25	≥1990	31	33	247	263	≤180
N35UH	11.7	12.1	1.17	1.21	10.8	11.5	860	915	≥25	≥1990	33	35	263	279	≤180
N38UH	12.2	12.6	1.22	1.26	11.4	12	908	955	≥25	≥1990	35	38	279	303	≤180
N40UH	12.6	12.9	1.26	1.29	11.8	12.4	940	987	≥25	≥1990	38	40	303	319	≤180

N26EH	10	10.4	1	1.04	9.6	10.2	764	812	≥30	≥2388	24	26	191	207	≤200
N28EH	10.4	10.8	1.04	1.08	9.8	10.4	780	811	≥30	≥2388	26	28	207	223	≤200
N30EH	10.8	12.2	1.08	1.12	10.1	10.6	804	844	≥30	≥2388	28	30	223	239	≤200
N33EH	11.2	11.6	1.12	1.16	10.4	11	828	876	≥30	≥2388	30	33	239	263	≤200
N36EH	11.7	12.1	1.17	1.21	10.8	11.5	860	915	≥30	≥2388	33	36	263	287	≤200

Keywords:

China Ningbo rare earth permanent magnet manufacturer and supplier, Chinese manufacturer of Magnet, China exporter of magnet, NdFeB magnet, Ferrite magnet, AlNiCo magnet, SmCo magnet, Flexible magnet, Rubber Magnet, speaker magnet, electomotor magnet, Servo magnet, step magnet, seperator magnet, ring magnet, radiaton magnet, disk magnet, permanent magnet made in china, Rare earth magnet in China, tile magnet, therapy magnet, Neodymium magnet, Neodymium ferrite boron permanent magnet, sintered NdFeB magnet, bonded NdFeB magnet, hard ferrite, ceramic ferrite, magnetic material, magnetic technology, China rare earth permanent magnet factory, China rare earth permanent magnet production base

Copyright© 2002-2006, Ningbo Vastsky Magnet Co.,Ltd. All rights reserved.